

PCT

WORLD INTELLECTUAL
PROPERTY ORGANIZATION



INTERNATIONAL APPLICATION PUBLISHED

(51) International Patent Classification ⁶ :

A61M 25/00

A1

(11) International Publication Number:

WO 96/04951

(43) International Publication Date:

22 February 1996 (22.02.96)

(21) International Application Number: PCT/IB95/00597

(22) International Filing Date: 31 July 1995 (31.07.95)

(30) Priority Data:
08/290,075 15 August 1994 (15.08.94) US

(71) Applicant: SCHNEIDER (USA) INC. [US/US]; 5905 Nathan Lane, Plymouth, MN 55442 (US).

(72) Inventor: ROYCHOWDHURY, Suranjit; Apartment 301, 10111 Cedar Lake Road, Minnetonka, MN 55305 (US).

(74) Agents: SPIEGEL, Allen, J. et al.; Pfizer Inc., Paten Dept., 235 East 42nd Street, New York, NY 10017 (US).

(81) Designated States: AU, CA, DE (Utility model), JP, MX, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).




Published

*With international search report.
Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.*

(54) Title: NON-COEXTRUSION METHOD OF MAKING MULTI-LAYER ANGIOPLASTY BALLOONS

(57) Abstract

A non-coextrusion process for making multi-layer angioplasty balloons involves pre-forming separate parisons (10, 12) and then concentrically disposing the plural parisons to form a composite parison which is then subjected to a blow-molding process. The resulting balloon can have its properties tailored by appropriate selection of the particular plastics to be used for the multiple parisons.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

NON-COEXTRUSION METHOD OF MAKING
MULTI-LAYER ANGIOPLASTY BALLOONS

BACKGROUND OF THE INVENTION

I. Field of the Invention:

5 This invention relates generally to balloon catheters and more particularly to methods for fabricating a multi-layer balloon composite exhibiting enhanced characteristics attributable to the properties of the individual layers comprising the balloon.

10 II. Discussion of the Prior Art:

 In the Hamlin patent 5,270,086, there is described a method for fabricating multi-layer composite expander members (balloons) for use on angioplasty and other types of balloon catheters. As is pointed out in the Hamlin
15 patent, by selective choice of the materials comprising the individual layers on the multi-layer balloon, the characteristics on the resulting balloon product can be tailored to overcome drawbacks of various polymer materials that have been used in the past in creating single layer
20 balloons. For example, a balloon fabricated from polyethylene terephthalate exhibits excellent burst strength and rupture properties with a desirable low distensibility, but it is difficult to bond such a balloon to a catheter body. By first extruding a tubular parison
25 from a polymeric material having good thermal bonding properties relative to the material of the catheter on which it is used and then co-extruding a layer of

-2-

polyethylene terephthalate (PET) on that parison, when the composite is subjected to a stretch blow-molding operation in a heated mold, a balloon results that allows ready thermal bonding to a catheter body.

5 It is also a desirable property of a expander member for an angioplasty catheter that its surface be lubricous. Lubricity may be added to a PET balloon by forming a three-layer tubular parison where, for example, PET is the intermediate layer provided for its high burst strength,
10 low distensibility and known rupture characteristics, an inner polyethylene layer to enhance bondability to a catheter body, and an co-extruded outer layer of a polymer, such as polycaprolactam, which is hydrophilic and exhibits low frictional resistance when passed through the vascular
15 system.

 Further information concerning the advantages and properties of co-extruded expander members for medical catheters are set forth in published Patent Cooperation Treaty application WO92/19316 and published European
20 application 553,960A1.

 The formation of multi-layer balloons using co-extrusion processes often times results in high rejection rates. It is somewhat difficult to maintain uniform layer thicknesses which may result in unacceptable variations in
25 the wall thickness of the resulting balloons once they are formed in a stretch blow-molding operation. Moreover, once parisons for the fabrication of multi-layer expander members are manufactured using a co-extrusion process, the

-3-

number of layers, their thicknesses and relative positions are fixed. The only way to vary these parameters would be to carry out additional extrusion runs, which is both time-consuming and expensive. In that each extrusion run generates a certain minimum quantity of parison lengths, process iterations cause manufacturing costs to escalate rapidly. It can also be appreciated that the prior art co-extrusion processes are quite inflexible in terms of being able to step through a number of possible multi-layer configurations quickly. Finally, co-extrusion is recognized as a more expensive process than the standard, single polymer extrusion process.

The method of the present invention obviates many of the foregoing drawbacks of the prior art co-extrusion processes for fabricating expander members for angioplasty and other medical catheters. Specifically, following the methods of the present invention materially increases the yield of acceptable multi-layer balloons without materially increasing the manufacturing cost thereof.

SUMMARY OF THE INVENTION

Rather than creating parisons for multi-layer expander members for use with medical catheters using co-extrusion techniques, in accordance with the present invention a first plurality of tubular parisons, made of a polymeric material having first physical properties, are formed in a single layer extrusion process with the extruded material having predetermined I.D. and wall thickness dimensions and being cut into multiple segments of desired lengths. A

-4-

second plurality of tubular parison, made of a polymer or polymer blend having second physical properties and dimensions is likewise formed in a single layer extrusion process. The outer diameter of the second plurality of parisons is greater than the outer diameter of the first plurality of tubular parison and the I.D. of the latter is slightly greater than the O.D. of the first set of parisons. One of the second group of tubular parisons is then concentrically disposed in telescoping relation with respect to one of the first tubular parison to form a composite parison. If desired, other tubular parisons may be similarly formed and coaxially disposed about the first two in creating a three layer configuration. The composite parison is heated and then subjected to a blow-molding operation in a mold to form a multi-layer expander member. The heating of the composite parison and expansion of this parison in the mold acts to thermally bond the adjacent layers of the multi-layer expander member to one another.

In accordance with a second manufacturing method, a multi-layer expander member for an angioplasty catheter is formed by first coaxially placing an outer polymeric sleeve of a length corresponding to the size of the balloon to be formed over a second, longer, extruded parison having a predetermined outer diameter. The polymers chosen for the inner and outer tubes will typically exhibit differing physical properties. The composite parison is then heated to a predetermined temperature prior to or when placed in a split mold, at which point a fluid is blown into the

-5-

inner parison to radially expand it as it is longitudinally stretched within the mold to expand both it and the surrounding outer sleeve to biaxially orient the inner member and bond the inner and outer members together in
5 creating a multi-layer expander member.

Those skilled in the art can appreciate that the method of the present invention offers significantly greater flexibility than the prior art co-extrusion process in that it permits mixing and matching of layers by
10 selecting a series of preformed single layer parisons. Further, the number and thicknesses of the layers can be easily varied by judiciously selecting pre-formed, single layer parisons and placing them in a coaxial relationship prior to the blow-molding operation. Thus, design
15 optimization to identify the optimum multi-layer configuration can be carried out quickly. Hence, design changes are readily achieved.

The entire rationale of the co-extrusion step in the formation of a parison to be used in creating a multi-layer
20 expander member for an angioplasty catheter or the like is to bond multiple layers together into a single entity or parison. This is a separate and distinct step before that of actually blowing a multi-layer balloon. In accordance with the present invention, the joining of the various
25 layers together and the blowing of the expander member itself preferably occurs in a single step.

DESCRIPTION OF THE DRAWINGS

The foregoing features, objects and advantages of the invention will become apparent to those skilled in the art from the following detailed description of a preferred embodiment, especially when considered in conjunction with the accompanying drawings in which:

Figure 1 depicts a process flow chart illustrating the steps in creating a multi-layer expander member for a "balloon" catheter in accordance with the present invention; and

Figure 2 illustrates the manner in which the method of Figure 1 is implemented.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

Referring to the process flow diagram of Figure 1 and the greatly enlarged views of Figure 2, the first step in the process is to create a first tubular parison of a first polymeric material having a predetermined length, I.D. and wall thickness. This step may be carried out by extruding a tube of the first material so that it possesses a desired inner diameter (I.D.) and wall thickness and then cutting the extruded tube to desired lengths for installation in a stretch/blow-molding fixture. Alternatively, a tube of the desired material may be extruded, cut to a given length and then mounted on a mandrel and necked down by stretching the tube on the mandrel until the desired I.D. and wall thickness are achieved. Without limitation, the wall thickness of the first tubular parison may be in the range of from 0.018 to

-7-

0.030 inch (0.046 to 0.076 cm) and a wall thickness variation less than 10% and preferably between about 3% and 0%.

The particular polymeric material chosen for the first
5 or outer tubular parison 10 is based upon the desired physical properties for the innermost layer of the expander member to be formed. For example, if a polyester, such as PET, is to be used as the material for one of the layers of the composite expander member to be formed because of its
10 desirable burst strength and rupture properties, and the expander member is to be affixed to a catheter body comprising a polyether block amide (PEBA), to enhance the bondability of the composite balloon to the catheter body, the plastic of the innermost layer may, for example, be
15 polyvinyl chloride which more readily bonds to each.

As is illustrated by step B of the drawing, the next step in the process is to create a second plurality of tubular parisons from a polymeric material different from the first. The material is again selected for physical
20 properties that synergistically combine with the physical properties of the first tubular parison. Here again, the second tubular parison 12 may be formed by extruding same to a desired outer diameter which is slightly less than the I.D. of the first tubular parison. The extrusion may then
25 be cut to a predetermined lengths which may be equal to or less than the lengths of the first tubular parisons.

As was the case with the formation of the first tubular parisons, rather than extruding a tube to the

desired I.D., it may be somewhat oversized and then placed on a mandrel having an O.D. equal to the desired I.D. of the second tubular parisons and then necked down in a stretching operation until it conforms to the O.D. of the mandrel and is of the desired wall thickness. The mandrel can then be removed and the tube cut to yield plural parisons of the designed length. The wall thickness of the second parisons may typically be in the range of from 0.005 to 0.015 inch (0.013 to 0.038 cm), again with a thickness variation of under 10% and preferably between 0% and 3%.

Once the first and second parisons are formed, one of each are coaxially disposed in overlapping relationship as shown in Step C of Figure 2 so that the first tubular parison surrounds the second. While the process thus far described contemplates only two coaxially disposed tubular parisons, those skilled in the art can appreciate that the method can be extended to three or more layers by merely creating additional tubular parisons of an appropriate size so that they can be telescopically disposed relative to one another in a predetermined order. For example, if the polymeric materials chosen for the first and second tubular parisons tend not to bond well to one another, a third parison, compatible with each, can be formed and dimensioned so as to fit between the outermost and innermost parisons when the three are telescopically disposed relative to one another.

As is reflected by step D in the flow chart, the composite parison of step C is heated to a temperature that

-9-

is above the transition temperatures of the polymeric materials selected for the inner and outer layers. The heating step may be accomplished within or external to the mold 14 (Figure 2) used in carrying out step E of the process. In step E, the product of step D is subjected to a stretch/blow-molding operation commonly used in creating single layer angioplasty expander members. Because of the coaxial disposition of the first and second tubular parisons, during the stretch/blow-molding operation, a multi-layer expander member of a predetermined length, O.D., and wall thickness results. That expander member exhibits the physical properties that are a combination of those of the chosen polymeric materials and their relative coaxial position relative to one another.

As those skilled in the art appreciate, all elements of the composite parison are longitudinally and radially expanded during the stretch/blow-molding operation to biaxially orient the molecules thereof. This is conventionally accomplished by using a split mold 14 which permits the drawing or stretching of the composite parison in the longitudinal direction while, at the same time, injecting a suitable fluid, under pressure, to radially expand the materials so that they conform to the cavity of the mold. By properly establishing the wall thickness of the parison layers, the radial size of the mold cavity and the amount of longitudinal stretching employed, it is possible to create expander members having predetermined

-10-

characteristics including burst strength, extensibility or compliance, O.D. and creep.

From what has been thus far described, it is apparent that a wide variety of polymeric materials may be selected
5 for pre-forming the parisons. During production of balloons, different combinations and orientations of the pre-formed parisons can be selected to create composite expander members exhibiting desired properties. The ability to mix and match and thereby tailor the properties
10 of the end product is an important advantage of the method of the present invention.

While the steps illustrated in Figures 1 and 2 involve only two separate parisons concentrically disposed relative to one another, it can be appreciated that additional
15 layers may be added as well. For example, if it is desired to decrease the coefficient of friction of the outer exposed surface of the balloon, a tubular parison of a hydrophilic polymer such as polycaprolactam, polyvinylindol and vinyl pyrrolidone may be pre-formed and then fitted
20 over the assembly of Step C before the resulting composite parison is heated and stretch blow-molded as in Steps D and E. The polymer of one of the intermediate layers would typically be selected for its tensile properties and, without limitation, may consist essentially of a material
25 selected from the group including ABS (acrylonitrile-butadiene-styrene), ABS/Nylon, ABS/PBC, ABS/polycarbonate and combinations thereof, acrylonitrile copolymer, polyacrylamide, polyacrylate, polyacrylsulfone,

-11-

polyethylene terephthalate (PET), polybutylene terephthalate (PBT), polyethylene naphthalate (PEN), liquid crystal polymer (LCP), polyester/polycaprolactone, polyester/polyadipate, polyetheretherketone (PEEK),
5 polyethersulfone (PES), polyetherimide (PEI), polyetherketone (PEK), polymethylpentene, polyphenylene ether, polyphenylene sulfide, styrene acrylonitrile (SAN), Nylon 6, Nylon 4/6, Nylon 6/6, Nylon 6/66, Nylon 6/9, Nylon 6/10, Nylon 6/12, Nylon 11 and Nylon 12. The innermost
10 layer may be selected for abrasion-resistance and may comprise nylon, a polyurethane or a polyamide copolymer.

If the inner layer resulting from the coaxially arranged parison is intended to enhance the bonding characteristics of the resulting balloon to a catheter
15 body, it may comprise a plastic material selected from the group consisting of ethylene, propylene, ethylene vinyl acetate, and ethylene vinyl alcohol (EVA), various ionomers, polyethylene type I-IV, polyolefins, polyurethane, polyvinyl chloride and polysiloxanes
20 (silicons).

It can be appreciated that the process of the present invention can be used to combine a variety of materials, each having distinct physical properties, e.g. one for its burst strength and distensibility, another for its
25 bondability to a range of different plastics, another for its lubricity and freedom from pinholes, etc.

The process outlined in the steps of Figures 1 and 2 can be slightly modified in creating a multi-layer parison

-12-

by simultaneously necking down separate, multiple extruded telescoping tubes of different polymers onto a common mandrel having an outside diameter equal to the inside diameter required of the composite parison from which the
5 balloon is to be blown. That assembly is heated in a way to ensure adhesion of the different layers over the entire length that is to be used in the expander blowing step, i.e., the entire parison length that will be gripped, stretched and blown.

10 In a different process, one or more relatively short sleeves of a selected polymeric material is/are slipped over the outside of a longer base parison. The length of the sleeve is such that it occupies only the balloon blowing cavity of the split mold 14 used in the stretch/
15 blow-molding step. The heat and radial pressure of the blowing process is used to ensure adhesion of the sleeve or sleeves to one another and to the base parison. Thus, a base parison is crated by extruding a tube to a desired I.D. and O.D. or by necking down a tube onto a mandrel
20 whose outside diameter is equal to the desired inside diameter of the parison being formed and until the wall thickness thereof reaches a desired value. The mandrel is then removed and a pre-formed, relatively short, tubular sleeve is fitted over the base parison before the
25 resulting composite is inserted into the mold in which the stretch blow-molding operation is to take place. Again, the mold is heated to the desired transition point for the polymers involved and the base parison is drawn

-13-

longitudinally and a fluid is injected into it to radially expand the base parison and with it, the surrounding sleeve, to cause them to conform to the walls of the cavity formed in the mold. Again, those skilled in the art can appreciate that more than one sleeve can be concentrically disposed about the base parison to appropriately tailor the physical properties of the resulting catheter expander member.

This invention has been described herein in considerable detail to comply with the Patent Statutes and to provide those skilled in the art with the information needed to apply the novel principles and to construct and use such specialized components as are required. However, it is to be understood that the invention can be carried out by specifically different equipment and devices, and that various modifications, both as to the equipment details and operating procedures, can be accomplished without departing from the scope of the invention itself.

What is claimed is:

-14-

CLAIMS

1. A method of manufacturing a multi-layer expander member for an angioplasty catheter comprising the steps of:

- a) forming a first tubular parison (10, 12) of
5 a polymer having first physical properties;
- b) forming a second tubular parison (12, 10) of a polymer having second physical properties;
- c) disposing one of said first and second tubular parisons (10, 12) over the other of said first and
10 second tubular parisons (10, 12) to form a composite parison;
- d) heating said composite parison to a predetermined temperature; and
- e) blow-molding said composite parison in a
15 mold (14) having a cavity of a predetermined length and radial dimension to form said multi-layer expander member.

2. The method as in Claim 1 and further including the step of longitudinally stretching said composite parison simultaneously with the blow molding thereof.

- 20 3. The method as in Claim 1 wherein said first tubular parison (10, 12) has a wall thickness in the range of from 0.018 and 0.030 inch and said second tubular parison (12, 10) has a wall thickness in the range of from 0.005 to 0.015 inch.

- 25 4. The method as in Claim 3 wherein a variation in wall thickness over the length of each of said first and second parisons (10, 12) is under 10 percent.

-15-

5. The method as in Claim 4 wherein said variation in wall thickness of said first and second parisons (10, 12) is preferably between 3 percent and 0 percent.

6. The method as in claim 1 wherein heating of said
5 composite parison thermally bonds adjacent layers of said multi-layer expander member to one another.

7. The method as in claim 6 wherein said first tubular parison (10, 12) is formed from a polyester material and said second tubular parison (12, 10) is a
10 polyamide.

8. The method as in claim 6 wherein said first tubular parison (10, 12) is polyethylene terephthalate and said second tubular parison (12, 10) is an abrasion resistant polymer material.

9. The method as in Claim 8 wherein said abrasion
15 resistant polymer material is selected from the group including Nylon 6, Nylon 12, Nylon 6/6, polyethylene and polyurethanes.

10. The method as in Claim 6 wherein said second
20 tubular parison (12, 10) comprises a tubular sleeve shorter in length than said first tubular parison (10, 12).

11. The method as in Claim 10 wherein said tubular sleeve is of a length equal to the predetermined length of the cavity of the mold (14).

12. The method as in Claim 11 wherein a fluid is
25 introduced under pressure into said first tubular member (10, 12) in said blow-molding step to radially expand said

-16-

first tubular parison (10, 12) into intimate contact with said tubular sleeve to fuse the two together.

13. The method of Claim 1 and further including the steps of:

5 a) forming a tubular member of a polymer thermally bondable to said first and second tubular parisons (10, 12); and

 b) concentrically disposing said tubular member between said first tubular parison (10, 12) and said second
10 tubular parison (12, 10) prior to the stretch blow-molding step.

14. The method of Claim 13 wherein said polymer of said tubular member is selected from the class including ethylene propylene, ethylene vinyl acetate and ethylene
15 vinyl alcohol, polysiloxanes, polyethylene and copolymers thereof, polyolefins, polyurethane, polyvinyl chloride, polychloratriethylene, ethyl tetrafluoroethylene, polyamides.

15. A method of manufacturing a multi-layer expander
20 member for an angioplasty catheter comprising the steps of:

 a) telescopingly placing an inner (12) and an outer (10) polymer tube, each of differing physical properties, onto a cylindrical mandrel having a predetermined outer diameter;

25 b) simultaneously stretching said inner (12) and outer (10) polymer tubes to conform to said outer surface of said cylindrical mandrel to provide a

-17-

predetermined total wall thickness for said inner (12) and outer (10) polymer tubes;

c) removing said inner (12) and outer (10) polymer tubes from said mandrel yielding a composite parison, said composite parison having a lumen corresponding to said outer diameter;

d) heating said composite parison to a predetermined temperature; and

e) expanding said composite parison both longitudinally and radially within a mold to biaxially orient and bond the polymer material comprising said inner and outer polymer tubes together.

16. The method as in Claim 15 wherein said step of expanding said composite parison radially comprises injecting a fluid under pressure into said lumen.

17. The method as in Claim 15 wherein said step of expanding said composite parison both longitudinally and radially includes simultaneously injecting a fluid under pressure into said lumen and longitudinally stretching said composite parison.


18. The method of Claim 15 wherein said inner polymer tube is formed from a thermoplastic selected from the group including polyethylene terephthalate, acrylonitrile-butadiene-styrene (ABS) and ABS/polycarbonate copolymers.

19. The method of Claim 15 wherein said outer polymer tube is formed from a thermoplastic selected from the group including nylon, polyether block amide, polyethylene





-18-

polyurethane, and polyvinyl chloride polycaprolactam,
polyvinylindol and N-vinyl-pyrrolidone.

1/2

FIG. 1

2/2

FIG. 2A**FIG. 2B****FIG. 2C****FIG. 2D**

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/IB 95/00597

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 A61M25/00

According to International Patent Classification (IPC) or to both national classification and IPC:

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 A61M B29C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP,A,0 457 456 (BARD) 21 November 1991 see the whole document ---	1-3, 6-13, 15-19
A	US,A,5 270 086 (HAMLIN) 14 December 1993 cited in the application see column 2, line 31 - column 68; figures ---	1,8,9, 14,15,18
A	US,A,4 775 371 (MUELLER) 4 October 1988 see column 1, line 61 - column 2, line 68; figures -----	1,15

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- 'A' document defining the general state of the art which is not considered to be of particular relevance
- 'E' earlier document but published on or after the international filing date
- 'L' document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- 'O' document referring to an oral disclosure, use, exhibition or other means
- 'P' document published prior to the international filing date but later than the priority date claimed

- 'T' later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- 'X' document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- 'Y' document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- 'A': document member of the same patent family

Date of the actual completion of the international search

18 January 1996

Date of mailing of the international search report

25.01.96

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel: (+31-70) 340-2040, Tx. 31 651 epo nl.
Fax: (+31-70) 340-3016

Authorized officer

Kousouretas, I

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No.
PCT/IB 95/00597

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-457456	21-11-91	AU-B- 7524391 JP-A- 4231070 US-A- 5358486	21-11-91 19-08-92 25-10-94
US-A-5270086	14-12-93	AU-B- 626103 AU-B- 6317290 CA-A, C 2025962 DE-T- 69002295 EP-A, B 0420488 ES-T- 2043289 JP-A- 3205064 NO-B- 178424	23-07-92 28-03-91 26-03-91 04-11-93 03-04-91 16-12-93 06-09-91 18-12-95
US-A-4775371	04-10-88	NONE	